Primers

RZ - 900 Plastic Primer

Product Description

Single - component primer to promote adhesion of paint to plastic parts.
Suitable for PP, ABS, PA or PVC plastic substrates.

Technical Characteristics

Color: Transparent Shelf life: 24 months at 25°C Theoretical spreading rate: 30 - 60 m² /l (avg) at 1 um

Pre-treatment

Degrease with RZ - AX800.
Wash off residues and dry thoroughly.
Re - clean with RZ - AX800.The use of a tack rag is recommended.
Plastic substrates except PE should be wet flat with P600 - 800 grade paper or dry flat with P320 - 400 grade paper.

Mixing Ratio	This product is ready for use.
Potlife **Spray Viscostiy**	to 1 econ DIN 4 cup a °C hours 25
Sprayguns	HVLP gravity - feed spraygun 1.2 - 1.3 mm 1.5 - 2.0 bar 10 - 15 cm Conventional gravity - feed spraygun 1.3 - 1.6 mm 3.0 - 4.0 bar 15 - 20 cm
Application	Number of spraycoats: 2 thin coats Flash - off: 5 - 10 mins Film thickness: 5 - 10 µm
Drying	Dust free at 25°C: 15 - 20 mins
Further Treatment	Atier the dust - free, apply Reiz RZ - 1K/2K Primer.

REIZ Automotive Refinish

The products are suitable for professional use only. The data contained in this publication are based on our current knowledge and experience.
Youcan obtain the latest version of technical date sheet from our website at www.wonder-global.com or directly from your supplier.