

Primers

RZ - 972-2 1K Primer Surfacer (White)

Product Description

Fast - drying primer surfacer for covering minor defects on putty/existing finishes.

Technical Characteristics

Color: Grey Shelf life: 24 months at 25°C Theoretical spreading rate: 240 - 280 m²/l (avg) at 1 µm


Pre-treatment

Degrease with RZ - AX800.

Wash off residues and dry thoroughly.

Re-clean with RZ - AX800. The use of a tack rag is recommended.

Wet flat with P600 - 800 grade paper or dry flat with P240 - 360 grade paper.

	Mixing Ratio	RZ - 972-2 Primer	100 (vol)	100 g
		RZ - 944 Super Fast Thinner	140 - 150 (vol)	100 - 110 g
		d st n before ap atton.		
	Spray Viscosity Potlife	to 20 on at °C 24 hours at 25°C		
	Sprayguns	HVLP gravity - feed spraygun	1.5 - 1.7 mm	1.8 - 2.0 bar
		Conventional gravity - feed spraygun	1.6 - 1.8 mm	3.0 - 4.0 bar
	Application	Number of spraycoats: 1 thin + 1 wet coat Flash - off: 5 - 8 mins Film thickness: 60 - 80 µm		
	Drying	Drying	25°C	60°C
		Dust free atter	10 mins	-
		Fully cured atter	30 - 45 mins	10 - 15 mins
Further Treatment		Atter the dust-free, apply Reiz basecoat or topcoat.		

The products are suitable for professional use only. The data contained in this publication are based on our current knowledge and experience. You can obtain the latest version of technical data sheet from our website at www.wonder-global.com or directly from your supplier.