



A 2017 Plastic Particle Topcoat

## **Product Description**

Double-component Plastic Particle Topcoat plastic parts repair . Suitable for PP, ABS, PA or PVC plastic substrates.

## **Technical Characteristics**

Color: Black Shelf life: 24 months at 25°C Theoretical spreading rate: 280 m²/l (avg) at 1 um/ 8 m²/l (avg) at 40 um

## Pre-treatment

Suitable for PP, ABS, PA or PVC plastic substrates & 2K Primer Unsuitable for putty and PE Degrease with RZ-800 (Degreser).

Wet sanding with P600-800

Dry sanding with P400-600



Mixing Ratio

A 2017 Plastic Particle Topcoat A 2017H Hardener 100 (vol) 25 (vol) 100 g 25 g

RZ-T50 Thinner

5-10 (vol)

4-8g



Spray Viscosity Potlife 50 to 60 seconds DIN 4 cup at 25°C

1 hours at 25°C



**Sprayguns** 

HVLP gravity-feed spraygun

1.3 – 1.4 mm 1.8

1.8 - 2.0 bar 15 - 25 cm

Compliant gravity-feed spraygun

1.3 - 1.6 mm 3.0 - 4.0 bar

15 - 20 cm

## **Application**

Maximum fan area

Note: Particle size were control by spray distance and air out put:

Maximum particle: spray distance: 25cm

air out put: Knop 1 laps

Air pressure: 1.8 - 2.0 bar

Minimum particle: spray distance: 20

air out put : Knop 1.5 laps

Air pressure: 2.5 - 3.0 bar



**Application** 

Number of spraycoats: 1 half wet + 1 half wet

Flash-off: 5 - 8 mins

Total Film thickness: 40 um



Drying

Drying 25°C 60°C

Dust free after 5 mins –

Ready for assembly after 25 mins 15 mins

The products are suitable for professional use only. The data contained in this publication are based on our current knowledge and experience. You can obtain the latest version of technical date sheet from our website at <a href="www.wonder-global.com">www.wonder-global.com</a> or directly from your supplier.

