

Thinners

Reiz Thinners

Product Description

Used to reduce application viscosity and to increase the smoothness of the paint film. Thinner with high dissolving ability, compatible with InnoColor primers, basecoats, topcoats and clears.

**RZ - T40 Thinner 5°C - 15°C (Fast) RZ - T50 Thinner 15°C - 25°C (Standard) RZ - T60 Thinner 25°C - 35°C (Slow)
RZ - T70 Thinner >35°C (Extra Slow)**

Technical Characteristics

Color: Transparent Shelf life: 48 months at 25°C

Pre-treatment

As specified in the TDS of the products in which RZ Thinner is being used.

	Mixing Ratio	Stir well before use.																					
		<table border="0"> <tr> <td>RZ - 981 Primer</td> <td>100 (vol)</td> <td>100 g</td> </tr> <tr> <td>RZ - 961 Hardener</td> <td>25 (vol)</td> <td>20 g</td> </tr> <tr> <td>RZ - T40/T50/T60/T70 Thinner</td> <td>50 - 60 (vol)</td> <td>30 - 35 g</td> </tr> <tr> <td>2K Solids/Clears</td> <td>100 (vol)</td> <td>100 g</td> </tr> <tr> <td>RZ - T40/T50/T60/T70 Thinner</td> <td colspan="2">depending on 2K Solids/Clears</td> </tr> <tr> <td>RZ - 972-2 Primer</td> <td>100 (vol)</td> <td>100 g</td> </tr> <tr> <td>RZ - 944 Super Fast Thinner</td> <td>140 - 150 (vol)</td> <td>100 - 110 g</td> </tr> </table>	RZ - 981 Primer	100 (vol)	100 g	RZ - 961 Hardener	25 (vol)	20 g	RZ - T40/T50/T60/T70 Thinner	50 - 60 (vol)	30 - 35 g	2K Solids/Clears	100 (vol)	100 g	RZ - T40/T50/T60/T70 Thinner	depending on 2K Solids/Clears		RZ - 972-2 Primer	100 (vol)	100 g	RZ - 944 Super Fast Thinner	140 - 150 (vol)	100 - 110 g
RZ - 981 Primer	100 (vol)	100 g																					
RZ - 961 Hardener	25 (vol)	20 g																					
RZ - T40/T50/T60/T70 Thinner	50 - 60 (vol)	30 - 35 g																					
2K Solids/Clears	100 (vol)	100 g																					
RZ - T40/T50/T60/T70 Thinner	depending on 2K Solids/Clears																						
RZ - 972-2 Primer	100 (vol)	100 g																					
RZ - 944 Super Fast Thinner	140 - 150 (vol)	100 - 110 g																					
	Mixing Ratio	<table border="0"> <tr> <td>1K Basecoats</td> <td>100 (vol)</td> <td>depending on colors</td> </tr> <tr> <td>RZ - T40/T50/T60/T70 Thinner</td> <td>100 - 120 g</td> <td></td> </tr> </table>	1K Basecoats	100 (vol)	depending on colors	RZ - T40/T50/T60/T70 Thinner	100 - 120 g																
1K Basecoats	100 (vol)	depending on colors																					
RZ - T40/T50/T60/T70 Thinner	100 - 120 g																						
	Application	<p>RZ-D603 chromed aluminium thinner for RZ-D707 tinters formula Mix well and strain before application. Note: If the temperature and humidity are too high, RZ - AX70 retarder solvent can be added.</p> <p>As specified in the TDS of the products in which RZ Hardeners are being used. Important: Due to different dissolving ability, it is recommended Reiz products should be used with RZ Thinner to ensure the best performance.</p> <p>Tips:</p> <ol style="list-style-type: none"> 1) Be cautious of over dissolution of the paint when using high - dissolving thinner. Avoid orange peel. 2) Be cautious of under dissolution of the paint when using poor - dissolving thinner. Avoid poor leveling and poor color effect (e.g. orientation of aluminum/pearl particles, poor solid color brightness). 																					

The products are suitable for professional use only. The data contained in this publication are based on our current knowledge and experience. You can obtain the latest version of technical data sheet from our website at www.wonder-global.com or directly from your supplier.