

Thinners

Reiz Thinners

Product Description

Used to reduce application viscosity and to increase the smoothness of the paint film. Thinner with high dissolving ability, compatible with InnoColor primers, basecoats, topcoats and clears.

RZ - T40 Thinner 5°C - 15°C (Fast) **RZ - T50 Thinner 15°C - 25°C (Standard)** **RZ - T60 Thinner 25°C - 35°C (Slow)**
RZ - T70 Thinner >35°C (Extra Slow)

Technical Characteristics

Color: Transparent Shelf life: 48 months at 25°C

Pre-treatment

As specified in the TDS of the products in which RZ Thinner is being used.



Mixing Ratio

Stir well before use.

RZ - 981 Primer	100 (vol)	100 g
RZ - 961 Hardener	25 (vol)	20 g
T50/T inn		30 - 35 g
ea	100 (l)	100 g
50/T hinn	depending on 2K Solids/Clears	



Mixing Ratio


1K Basecoats 100 (vol) depending on colors

RZ - T40/T50/T60/T70 Thinner 100 - 120 g

Mix well and strain before application.

Note: If the temperature and humidity are too high, RZ - AX70 retarder solvent can be added.

Automotive Refinish



Application

As specified in the TDS of the products in which RZ Hardeners are being used.

Important: Due to different dissolving ability, it is recommended Reiz products should be used with RZ Thinner to ensure the best performance.

Tips:

- 1) Be cautious of over dissolution of the paint when using high - dissolving thinner. Avoid orange peel.
- 2) Be cautious of under dissolution of the paint when using poor - dissolving thinner. Avoid poor leveling and poor color effect (e.g. orientation of aluminum/pearl particles, poor solid color brightness).

The products are suitable for professional use only. The data contained in this publication are based on our current knowledge and experience. You can obtain the latest version of technical data sheet from our website at www.wonder-global.com or directly from your supplier.