

1K Binders

RZ - S160 1K Balance Binder for Basecoat Color Preparation

Product Description

1K Binder for REIZ basecoats. Improves leveling and enhances orientation of aluminum and pearl particles. When S160 used in grey metallic colors, it can enhance the sprayed effect.

Technical Characteristics

Color: Milky

Shelf life: 24 months at 20°C

Pre-treatment

See process described in TDS of REIZ Basecoat - Solid Basecoat 2c, Metallic Colors 2c, Red Pearl 2c, Xirallic / Pearlescent Basecoat 3c.

	Mixing Ratio	Stir well before use. <table> <tr> <th></th><th></th><th>RZ - S160</th></tr> <tr> <td>RZ - 1K Solid Basecoat</td><td>100 g:</td><td>5 - 8 g</td></tr> <tr> <td>RZ - 1K Coarse Alu.</td><td>100 g:</td><td>5 - 8 g</td></tr> <tr> <td>RZ - 1K Fine Alu.</td><td>100 g:</td><td>5 - 8 g</td></tr> <tr> <td>RZ - XI/P Pearl</td><td>100 g:</td><td>5 - 8 g</td></tr> </table> Note: RZ - S160 can prevent the metallic color with cloudy phenomenon and get a perfect flake control in metallics.			RZ - S160	RZ - 1K Solid Basecoat	100 g:	5 - 8 g	RZ - 1K Coarse Alu.	100 g:	5 - 8 g	RZ - 1K Fine Alu.	100 g:	5 - 8 g	RZ - XI/P Pearl	100 g:	5 - 8 g
		RZ - S160															
RZ - 1K Solid Basecoat	100 g:	5 - 8 g															
RZ - 1K Coarse Alu.	100 g:	5 - 8 g															
RZ - 1K Fine Alu.	100 g:	5 - 8 g															
RZ - XI/P Pearl	100 g:	5 - 8 g															
	Spray Viscosity Potlife	to 1 econ DIN 4 cup															
	Application	See process described in TDS of REIZ Basecoat															
	Drying	See process described in TDS of REIZ Basecoat															
Further Treatment		See process described in TDS of REIZ Basecoat															

Automotive Refinish

The products are suitable for professional use only. The data contained in this publication are based on our current knowledge and experience. You can obtain the latest version of technical data sheet from our website at www.wonder-global.com or directly from your supplier.